

# SAC305 LEAD-FREE SOLDER ALLOY

# **FEATURES**

- Liquidus 220°C (428°F)
- Ocompatible with all Flux Types
- Excellent Wetting Speed
- Excellent Solderability and Spreading
- Reduced Bridging Versus Sn-Cu Alloys
- Nanufactured with AIM Electropure<sup>™</sup> Technology

# **DESCRIPTION**

SAC305 lead-free alloy contains 96.5 % tin, 3% silver, and 0.5% copper and is RoHS, REACH and JEIDA compliant. Applications include Wave, Selective, Hand and SMT Reflow Soldering. AIM Electropure<sup>™</sup> SAC305 bar solder offers reduced dross production and superior wetting and fluidity as compared to other solder brands. AIM's SAC305 bar solder is alloyed using our proprietary Electropure<sup>™</sup> method resulting in a low drossing, high wetting solder. AIM Electropure<sup>™</sup> SAC305 may be used with all existing lead-free compatible equipment, processes, coatings, and flux chemistries.

#### **AVAILABILITY**

SAC305 is available in 1.1 kg (2.5 lb) triangular bars, hanging AIM Safety Bar and Solid Wire. SAC305 is also available in AIM flux cored wire solders and solder pastes.

## **TYPICAL ALLOY COMPOSITION**

Typical Alloy Composition			
Sn: Balance	Ag: 3.0	Cu: 0.5	

## TYPICAL MELTING TEMPERATURE

Typical Melting Temperature			
Solidus: 217°C (423°F)	Liquidus: 220°C (428°F)		



## **HANDLING & STORAGE**

Parameter	Time	Temperature
Shelf Life	Indefinite	Room Temperature

Indefinite shelf life applies to solid solder. For other product categories, refer to those specific TDSs. Consult AIM SAC305 SDS for additional handling procedures and precautions.

## FLUX COMPATIBILITY

SAC305 bar solder is compatible with all major brands of noclean and water soluble electronic grade fluxes.

#### **SAFETY**

Use with adequate ventilation and proper personal protective equipment. Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

> Document Rev # NF2 Page 1 of 1

**DISCLAIMER** The information contained herein is based on data considered accurate and is offered at no charge. Product information is based upon the assumption of proper handling and operating conditions. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated. Please refer to http://www.aimsolder.com/terms-conditions to review AIM's terms and conditions.

WWW.AIMSOLDER.COM INFO@AIMSOLDER.COM