



Repulpable Double-Coated Splicing Tape

900

Technical Data

March, 2014

Product Description 3M™ Repulpable Double-Coated Splicing Tape 900 has a light-weight tissue coated on both sides with a blue, repulpable adhesive and furnished on a repulpable easy-release paper liner.

Product Construction	Adhesive	Liner	Color	Standard Roll Length
	Repulpable	Repulpable, semi-bleached kraft with easy-release treatment	Light blue	33 m (36 yds)

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Repulpability:	Tape – Completely* Liner – Completely*
Tape Thickness:	3.4 mils (0.09 mm) without liner
Bond Strength:	Delaminates most papers (including many LWC coating formulations, however adheres well to many other papers, too)
Heat Resistance:	Excellent to 400°F (204°C) web temperature

*Repulpability judged according to TAPPI UM-213, Procedure A.

Features

- Can be used for splicing of many LWC (light weight coated) papers, particularly for coated gravure papers. It has also performed well in many other finished splice applications, even with “alkaline coatings” and with stearate sizing.
- Packing in sealed plastic bags helps assure constant moisture content of unused tape.
- Water solubility and alkali dispersability are excellent and eliminate danger of contaminating the paper mill broke with non-repulpable material. (Poor quality paper and plugged Fourdrinier screens can be caused by non-repulpable, rubber-base splicing media.)
- All components of the adhesive and backing meet the requirements of indirect food additive regulations as described under 21 CFR 176.170 (Components of paper and paperboard in contact with aqueous and fatty food) and 21 CFR 176.180 (Components of paper and paperboard in contact with dry foods).

3M™ Repulpable Double-Coated Splicing Tape

900

Application Techniques For optimum results, firm, even rub down pressure must be applied to the taped area to create the best possible adhesion between the tape and paper surface. A plastic squeegee or similar tool can help achieve the proper uniform pressure.

Application Ideas

- Overlap finished splices in a paper mill (especially on many papers with LWC and other new coating formulations).
- Transfer (pull through) splices in Supercalenders.

Storage Store under normal conditions of 70°F (21°C) and 50% R.H. in the original carton.

Shelf Life To obtain best performance, use this product within 18 months from date of manufacture.

Product Use All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550 • 877-369-2923 (fax)
www.3M.com/industrial



Recycled Paper
40% pre-consumer
10% post-consumer

3M is a trademark of 3M Company.
Printed in U.S.A.
©3M 2014 (3/14)