

ESD Tape Applications





Wescorp ESD Tapes

In ESD protected areas, replace regular high charging tape with Wescorp ESD Tape. ANSI/ESD S20.20 section 8.3.1. states "All nonessential insulators, such as those made of plastics and paper (e.g., coffee cups, food wrappers and personal items) must be removed from the workstation."

Wescorp ESD Cellulose Tape Line



Technical Information for ESD Cellulose Tape

Film Thickness: 1.9 mil (0.048 mm) Film construction: Cellulose

Adhesive: Rubber based - non-staining, absorbs moisture Adhesive surface resistance: 1 x 10² to < 1 x 10⁵ ohms per

ANSI/ESD STM11.11

Film surface resistance: 1×10^9 to $< 1 \times 10^{11}$ ohms per

ANSI/ESD STM11.11

RoHS, REACH, and Conflict Minerals Statement

See the Desco Industries RoHS, REACH, and Conflict Minerals

Descoindustries.com/ROHS.aspx

See the Desco Limited Warranty:

Desco.Descoindustries.com/Limited-Warranty.aspx

See the Desco Disclaimer:

Desco.Descoindustries.com/Disclaimer.aspx

Temperature Range: -10°C to 71°C (14°F to 160°F)

100°C for 10 minutes max

Color: Transparent

Roll Length: 36 yards (1" core); 72 yards (3" core) Total Thickness: 2.4 mil 0.0024". (0.06mm)

Elongation: 22.5%

Tensile Strength: 22 lbs/in Adhesion Strength: 59oz/in²

Static Generation from conductive plate: (73°F, 45% RH): 80 volts average

Static Generation from roll:

(73°F, 45% RH): 50 volts average Available on paper cores and plastic cores

No Sulfur, sufactants, amines, or silicone based material (adhesive, film backing, release material) is used in the manufacture of Wescorp cellulose tape.

Applications for ESD Clear Cellulose Tape with and without Symbols

- Sealing ESD bags and other ESD packaging\ containers
- Use with ESD symbols for ESD awareness
- General purpose ESD tape applications
- Secure (bundle) IC DIP tubes
- · Prevents damage to sensitive electronic components in manufacturing
- Ideal for holding notes, work orders or instructions in offices, ESD workstations, or for general purpose
- Ideal for conformal coating or holding and sealing supplies in manufacturing
- Ideal in packaging for container sealing, static shielding bag closure and holding DIP tubes

Applications for ESD Clear Cellulose Tape with Symbols


- Identification or making product / paperwork / processes
- High visibility with ESD susceptibility symbol for increased awareness
- Attach paperwork to bags or to ESD susceptible product
- Ideal in packaging for container sealing, static shielding bag closure and holding IC DIP tubes

Note: Tape widths are metric (it applys to all 4 tape types).

Tape widths are nominal metric ± 0.8 mm ($\pm 1/32$ ")

- 1/4" is 6 mm nominal or 0.236"
- 1/2" is 12 mm nominal or 0.472"
- 3/4" is 18 mm nominal or 0.709"
- 1" is 24 mm nominal or 0.945"

DESCO INDUSTRIES INC • 3651 Walnut Avenue, Chino, CA 91710 • (909) 627-8178 • Web Site: Descolndustries.com





Wescorp ESD Conductive Shielding Grid Tape **Technical Information for Conductive Shielding Grid**

Both surfaces non-tribocharging at 50% RH Thickness: 1.9 mil 0.0019". (0.048mm)

Adhesive: acrylic based

Conductive grid layer (50% RH): 1×10^4 to $< 1 \times 10^6$ ohms

per ANSI/ESD STM11.11

Adhesive copolymer resistivity: 10⁹ ohms typical Copolymer layer resistivity: 10¹² ohms typical

Max Temperature: 140°F (60°C) Absence of shed, crack, chip, or rub off

Non-corrosive

No silicone based material (adhesive, film backing, releas material) is used in the manufacture of Wescorp conductive shielding grid tape.

Applications for Conductive Shielding Grid Tape

- For applications requiring EMI shielding
- Use in areas where the generation of static electricity is of concern
- Using grounded Tape Dispenser, voltage generated by unrolling will effectively be reduced to approaching
- Secure (bundle) IC tubes
- Cover external plugs, holes or connector pins on electronic chassis (black boxes, etc.) during transportation or storage

Excerpt from the Naval Aviation Schools Command: "... Weapon Replaceable Assemblies (WRA)s shall have ESD conductive plug caps or grid tape over all external cannon plugs and connector pins."

Wescorp ESD High-Temp Masking Tape

Technical Information for High-Temp Masking Tape

Backing: Saturated, high strength crepe paper

Adhesive: Natural rubber based, non-staining, solvent

spread, cured

Thickness: 7 mils (0.007") (0.18 mm) Adhesion Strength: 38 N/100 mm / 35 oz/in² Tensile Strength: 385 N/100 mm / 22 lbs/in²

Temperature Resistance: 302°F (150°C) - 60 minutes

Color: Natural

Meets CDN Spec.: 53.79-94 Type 1 Meets US Spec.: A-A 883-B-Type 1 Roll Length: 55 meters (60 yards) Thickness: 7.0 mils 0.007",(0.18 mm)

Adhesion to Steel: 1.51 newtons/cm² / 35 oz/inch²

Elongation: 8%

Moisture Resistance: fair Solvent Resistance: good Storage Stability: excellent

Temperature Range: -32°F to + 275°F (-36°C to + 135°C)

Max Temp: 275°F (135°C) 45 minutes maximum

Government Specs: PPP-T-42C Type 1, CID-AA-883A Type 1

Waterproof

Tribocharges, but no charge retention (recommend slow unrolling utilizing an ionizer to neutralize charges); recomend slow unwinding utilizing an ionizer to neutralize charges

Adhesive surface resistance: 10¹¹ ohms typical per ANSI/ ESD STM11.11

Non-toxic, and pH neutral

Non-corrosive

DESCO INDUSTRIES INC • 3651 Walnut Avenue, Chino, CA 91710 • (909) 627-8178 • Web Site: DescoIndustries.com

© 2020 DESCO INDUSTRIES INC TB-3010 Page 2 of 4

Normal use of our High Temperature Masking Tape is for masking or protective applications on printed circuit boards not exceeding temperatures of 150°C (302°F) at a duration under 45 minutes. If the tape is used for masking operations or temporary protection, it should not be left on the product for more than 24 hours. For best results, the tape should not be exposed to ultraviolet rays or high temperature for prolonged periods of time (beyond manufacturer's specs). This tape is non-staining under normal use as described above.

Applications for High-Temp Masking Tape

- Silk screening applications
- Masking application in spray and brush painting, non-staining
- Protective purposes in manufacturing processes, strips
- For securing polyethylene sheeting to walls during painting
- For OEM repair shops
- Use in applications masking PCBs gold features for wave soldering or soldering under 302°F (150°C)
- For best results, apply to board using a rubber roller.
- Thick conductive adhesive excellent for conformability to protect critical PCB features
- Easily handles high temperatures of wave soldering without leaving significant residue
- Handles temperatures found in test and burn-in ovens

Wescorp ESD High Temp Polyimide Tape



Technical Information for ESD High Temp Polyimide

Removal leaves little or no residue

Adhesive surface resistance: 1×10^2 to $< 1 \times 10^5$ ohms

per ANI/ESD STM11.11

Film Surface Resistance: 1 x 10⁸ to < 1x 10¹¹ ohms per

ANSI/ESD STM11.11

Max Temperature: 572°F (300°C) 10 seconds Adhesive Strength: 1 N/cm (DIN), 5 oz/inch² (ASTM) Polyimide Film (DuPont's Kapton® or equivalent)

Film Thickness: 1.0 mil (0.001") (0.0254 mm)

Conductive Silicone Adhesive

Overall Thickness: 1.4 mil (0.0014" (0.0356 mm) Total Thickness: 2.4 mil (0.0024") (0.060 mm)

Color: Brown Opaque

Tensile Strength: 50 N/cm (DIN), 28 lbs/in² (ASTM)

Elongation: 70% (DIN & ASTM)

Static Charge Generation (300 mm/min): Removal from Core (23°C, 50% RH):

5 volts. Internal Test Method

Removal from stainless steel (50% RH):

5 volts, Internal Test Method

Passed flammability per NASA STD 6001, Test 1 and Hypergol ignition and penetration testing for casual contact per MTB-175-88

For best results, apply to board using a rubber roller.

Applications for High-Temp Polyimide Tape

- Ideal for masking gold leads and other components on boards populated with sensitive integrated circuits
- · Thick conductive adhesive excellent for conformability to protect critical PCB features
- Near zero voltage generation when tape unrolled from roll [at 50% relative humidity]
- Near zero voltage generation when tape removed from PCB [at 50% relative humidity]
- Masking off PCBs for IR reflow ovens or wave soldering under $572^{\circ}F$ (300°C) ~ 10 seconds

Note: ESD High Temp Polymide Tape with conductive acrylic, adhesive (silicone free) is available as a special order.

Applications for Aisle Marking Tape

- Use to mark off floors designating ESD Protective Areas
- Can be used as area signs
- Note: Aisle marking Tape has no ESD control properties



DESCO INDUSTRIES INC • 3651 Walnut Avenue, Chino, CA 91710 • (909) 627-8178 • Web Site: DescoIndustries.com

© 2020 DESCO INDUSTRIES INC TB-3010 Page 3 of 4



Limited Warranty, Warranty Exclusions, Limit of Liability

See Desco's Terms and Conditions -Desco.DescoIndustries.com/TermsAndConditions.aspx

Tape Dispenser

2 inch wide ESD Tape Dispenser

- · Use with Wescorp ESD tapes
- For tape with 3" (7.62 cm) Cores
- For tapes rolls up to 2" (48 mm) wide (or combination of
- Groundable chassis with included ground cord

Wescorp Tape Storage:

For best results, tape inventory should be continually replenished. It is recommended that rolls of tape be stored flat and rotated (flipped over to the other side) periodically. Tapes should be stored in a dry, well ventilated room with a reasonably consistent temperature of 68°F (20°C) and be protected from exposure to direct sunlight. Tape should not be stored in ultraviolet sunlight, moisture, or heat. Tape over one year old should be evaluated by the user to determine acceptability for the user's application.

DESCO INDUSTRIES INC • 3651 Walnut Avenue, Chino, CA 91710 • (909) 627-8178 • Web Site: DescoIndustries.com

© 2020 DESCO INDUSTRIES INC TB-3010 Page 4 of 4