



## **FEATURES**

- Reduces the risk of bearing failure at high temperatures
- Resists carbonization at high temperatures
- Extends relubrication periods
- Excellent vibration resistance
- Very high dropping point
- Reduces grease consumption
- Reduces the need for multiple greases

## **APPLICATIONS**

- Aluminum Castings
- Boiler Room Equipment
- Crucibles

- Engine Room Equipment
- Processing Ovens
- Shrink Wrappers

# SPECIFICATIONS AND APPROVALS

• Timken Steel

# **PROPERTIES**

Appearance / Physical State	Solid/Paste		
Odor	Hydrocarbon-like		
Melting / Freezing Point	Not available		
Boiling Point / Range	Not available		
Base Oil Type	PAO/Mineral Oil		
Viscosity	525 SUS @ 100°F; 180 cst.@ 40°C; 12 cst. @ 100°C		
Copper Corrosion	1A/1B		
Dropping Point	536°F (280°C)		
NLGI Grade	2%		
Thickener Type	Lithium Complex		
Water Washout	<5%		
Color	Amber		
Flash Point	400.0°F (204.4°C) Cleveland Open Cup		
Density	0.87, 7.506 (lbs/gal) @ 15°C		
Evaporation Rate	Not available		
Vapor density	< 1 (air = 1)		
Auto-Ignition Temperature	Not available		
Specific Gravity	0.98		
Temperature Range	-15°F (-26°C) to 392°F (200°C)		
4-Ball Weld Load	>400 kg		

#### **DIRECTIONS**

For use in environments that require exceptionally high temperature resistance. Apply either manually or by a suitable applicator. For best results, bearings should be purged of their previous lubricant before introducing new grease.

### **HANDLING**

Observe good industrial hygiene practices.

### **STORAGE**

Store in original tightly closed container. Store away from incompatible materials (see Section 10 of the SDS).

## **DISPOSAL**

Collect and reclaim or dispose in sealed containers at licensed waste disposal site. Dispose of in accordance with local regulations. Empty containers or liners may retain some product residues. This material and its container must be disposed of in a safe manner.

## **AVAILABLE PRODUCTS**

Part No.				/6	
US	Canada	Net Contents	Container Type	Units/Case	Case Weight
70214	C70214	14.1 oz / 400 g	cartridge	30	32 lbs



800.241.8334 | www.itwprobrands.com