



<https://wearwell.com/>

Static Dissipative Anti-Fatigue

Group 791

Ideal for manufacturing and commercial areas where static electricity can pose a problem. A carbon-impregnated polyester scrim embedded in the surface ensures speedy dissipation of static electricity and a Nitricell sponge base ensures employee comfort and productivity.

- EOS/ESD S7.1: 1×10^6 - 1×10^9 (meets ANSI/ESD 20.20 requirements)
- "Best" sponge base
- Nitricell sponge base delivers 2X the resilience and 3X the life of typical sponges

NSFI Certified

- Lay-flat design and up to 20% more standing area than look-alikes
- Overall thickness 1/2"

Wearwell Categories Anti-Fatigue Matting

Suitable Environment Dry Floors

Customization Options C1 - Custom Length

Solid or Drainage Solid

Material PVC Surface With Nitrile Infused Sponge

Recycled <10%

Warranty 1 Year

| Property | Test / Result |
|-------------------------|--|
| Flammability | MVSS 302 / 'A'; Rating |
| Taber Abrasion | ASTM D 3884 / 1% loss |
| Temperature Range | 0 to 110 F |
| Coefficient of Friction | ASTM F1677 / Dry: COF = .62 / Wet: COF = .17 |
| Compression Deflection | ASTM D575 - 9/16 = 7.1psi @ 25% = .15" distance compressed |
| Tear Strength | Not Available |
| ESD Rating | EOS/ESD S7.1: 1×10^6 - 1×10^{10} (meets ANSI/ESD 20.20 requirements) |
| Dielectric Strength | Not Available |

| SKU | UPC | Color | Thickness | Dimensions | Stock Part | UOM |
|---------------|--------------|-------|-----------------|------------|------------|-----|
| 791.12x2x3GY | 715411441747 | Gray | 1/2 In. (13 mm) | 2' x 3' | Y | EA |
| 791.12x3x5GY | 715411442287 | Gray | 1/2 In. (13 mm) | 3' x 5' | Y | EA |
| 791.12x3x75GY | 715411442454 | Gray | 1/2 In. (13 mm) | 3' x 75' | N | RL |