



2 Ton® Epoxy

Description:	Extremely strong, medium-cure, water-resistant clear adhesive that will self-level after application.		
Intended Use:	Bonding parts in a structural environment or potting electronic components and assemblies.		
Features:	Cures without shrinking. Good impact resistance. Produces strong, rigid bond on metal, ceramics, wood, concrete, glass, or combinations.		
Typical Physical Properties:	Technical data should be considered representative or typical only and should not be used for specification purposes.		
	Cured 7 Days @ 75°F (24°C)	Typical Values	Standard Tests
	Adhesive Lap Shear (GBS)	2,250 psi (15.5 MPa)	Adhesive Lap Shear ASTM D1002
	Dielectric Strength	600 volts/mil (23.6 kV/mm)	Dielectric Strength ASTM D149
	Compression Strength	11,000 psi (75.8 MPa)	Compressive Strength ASTM D695
	Hardness	83 Shore D	Cured Hardness ASTM D2240
	Impact Resistance	6.5 ft. lb./in ² (13.6 kJ/m ²)	
	Service Temperature	-40°F - 200°F (-40°C - 93°C)	
	Solids by Volume	100	
	Specific Volume	25.2 in ³ /lb. (0.91 cm ³ /g)	
	Tensile Elongation	1%	
	T-Peel	2-3 pli (0.35 - 0.53 N/mm)	
	Uncured Properties @ 72°F (23°C)		
	Color	Clear	
	Working Time	8-12 minutes	
	Fixture Time	30-35 minutes	
	Functional Cure	2 hours	
	Full Cure	16 hours	
	Mix Ratio by Volume	1:1	
	Mix Ratio by Weight	1.2:1	
	Mixed Density	9.17 lb/gal (1.10 g/cm ³)	
	Mixed Viscosity	8,000 cP	
Surface Preparation:	Clean surface by solvent-wiping any deposits of heavy grease, oil, dirt, or other contaminants. Surface can also be cleaned with industrial cleaning equipment such as vapor phase degreasers or hot aqueous baths. If working with metal, abrade or roughen the surface to significantly increase the microscopic bond area and increase the bond strength.		
	Proper homogenous mixing of resin and hardener is essential for the curing and development of stated strengths.		
Mixing Instructions:	25 ML DEV-TUBE 1. Squeeze material into a small container the size of an ashtray. 2. Using mixing stick included on Dev-tube handle, vigorously mix components for one (1) minute. 3. Immediately apply to substrate.		
	50 ML/400ML CARTRIDGES 1. Attach cartridge to Mark V™ [50ml] 400ml manual or pneumatic dispensing systems. 2. Open tip. 3. Purge cartridge by squeezing out some material until both sides are uniform (ensures no air bubbles are present during mixing). 4. Attach mix nozzle to end of cartridge. 5. Apply to substrate.		
Application Instructions:	1. Apply mixed epoxy directly to one surface in an even film or as a bead. 2. Assemble with mating part within recommended working time. 3. Apply firm pressure between mating parts to minimize any gap and ensure good contact (a small fillet of epoxy should flow out the edges to display adequate gap fill.) For very large gaps: 1. Apply epoxy to both surfaces. 2. Spread to cover entire area OR make a bead pattern to allow flow throughout the joint. Let bonded assemblies stand for recommended functional cure time prior to handling.		
	CAPABILITIES: Can withstand processing forces Do not drop, shock load, or heavily load		
Storage:	Store in a cool, dry place. A shelf life of 3 years from date of manufacture can be expected when stored at room temperature (22°C)		

in their original containers. The expiry will be displayed on the product packaging.

Compliances: None

Chemical Resistance: Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F (24C)

Acetic 10% (Dilute)	Poor
Acetone	Fair
Ammonia	Very Good
Corn Oil	Excellent
Cutting Oil	Excellent
Ethanol	Poor
Gasoline (Unleaded)	Poor
Glycol/Antifreeze	Excellent

Hydrochloric 10%	Poor
Isopropanol	Poor
Kerosene	Excellent
Methyl Ethyl Ketone	Poor
Mineral Spirits	Excellent
Motor Oil	Excellent
Sodium Hydroxide 10%	Very Good
Sulfuric 10%	Poor

Precations: **FOR INDUSTRIAL USE ONLY:** Please refer to the appropriate Safety Data Sheet prior to using this product.

Warranty: ITW Performance Polymers will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Order Information:	Item No.	Package Size
	14310	25ml Dev-Tube™
	14260	50ml cartridge
	14355	400ml cartridge
	14360	9lb kit

Contacts:	www.itwpp.com	
	ITW Performance Polymers (US)	ITW Performance Polymers (EMEA)
	30 Endicott Street	Bay 150, Shannon Industrial Estate
	Danvers, MA 01923 USA	Shannon, County Clare, Ireland V14 DF82
	TEL: 855 489 7262	TEL: +353 61 771 500
	FAX: 978 774 0516	FAX: +353 61 471 285
	Email: info@itwpp.com	Email: customerservice.shannon@itwpp.com

Disclaimer: **Product Use:** The information herein is based upon good faith testing that ITW PP believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond ITW PP control and uniquely within user's knowledge and control can affect the use and performance of an ITW PP product in a particular application. Given the variety of influencers on performance, the data here is not intended to substitute end user testing. It is the end users sole responsible for evaluating any ITW PP product and determining whether it is fit for a particular purpose and suitable for user's design, production, and final application.

Exclusion of Warranties: As to the herein described materials and test results, there are no warranties which extend beyond the description on the face hereof. ITW PP makes no other warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. Since the use of the herein described involves many variables in methods of application, design, handling and/or use, the user, in accepting and using these materials, assumes all responsibility for the end result. ITW PP shall not otherwise be liable for loss of damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.