



KIMTECH PURE* G3 EvT Nitrile Glove, 12" Ambidextrous

Codes: 38700, 38701, 38702, 38703, 38704, 38705

Product Information

Code	Size	Palm Width*(mm)	Length* (mm)	Quantity
38700	XS	70	285	250 gloves/bag; 6 bags/case
38701	S	80	285	250 gloves/bag; 6 bags/case
38702	M	95	285	250 gloves/bag; 6 bags/case
38703	L	110	285	250 gloves/bag; 6 bags/case
38704	XL	112	285	250 gloves/bag; 5 bags/case
38705	XXL	120	285	250 gloves/bag; 5 bags/case

*As measured by ASTM D 6319; 2.5 AQL¹



Property	Description
General Description	Thin-mil, powder free, clear, clean room glove, nominal 12" length

Physical Property	Unit	Upper Limit	Test Method (1.5 AQL)
Watertightness	NA	Pass	ASTM D 5151
Particulate Level ≥0.5 microns	#/cm ²	950	IEST-RP-CC005

Extractable Ions	Upper Limit	Upper Limit	Test Method (1.5 AQL)
Calcium	40 µg/g	0.20 µg/cm ²	IEST-RP-CC005
Chloride	30 µg/g	0.15 µg/cm ²	IEST-RP-CC005
Magnesium	5 µg/g	0.03 µg/cm ²	IEST-RP-CC005
Nitrate	33 µg/g	0.17 µg/cm ²	IEST-RP-CC005
Potassium	5 µg/g	0.03 µg/cm ²	IEST-RP-CC005
Sodium	10 µg/g	0.05 µg/cm ²	IEST-RP-CC005
Sulfate	10 µg/g	0.04 µg/cm ²	IEST-RP-CC005
Zinc	25 µg/g	0.13 µg/cm ²	IEST-RP-CC005
Ammonium	5 µg/g	0.03 µg/cm ²	IEST-RP-CC005

Thickness	Nominal	Nominal	Test Method (2.5 AQL)
Middle Finger	5.00 mil	0.13 mm	ASTM D 6319
Palm	3.00 mil	0.08 mm	ASTM D 6319
Cuff	2.50 mil	0.06 mm	ASTM D 6319

Property	Tensile Strength	Ultimate Elongation	Median Force at Break
Before Aging	25 Mpa	500%	6.0 Newtons
After Aging	22 Mpa	450%	5.5 Newtons
Test Method (2.5 AQL)	ASTM D 412 ASTM D 573 ASTM D 6319	ASTM D 412 ASTM D 573 ASTM D 6319	ASTM D 412 ASTM D 573 ASTM D 6319

¹ AQL levels defined according to ISO 2859-1 (current edition) Sampling Procedures for Inspection by Attributes.

Workmanship Requirement: Gloves shall be made in accordance with reasonable industry practice with respect to defects, dirt and contamination. Gloves should be packaged as specified having described size and color in the appropriate quantity as listed. Shipping Case and inner packaging shall be labeled with product name, size, lot/batch and catalog number.

For additional information: 1-800-255-6401 or kimtech@kcc.com

Kimberly-Clark warrants that its products (1) comply with K-C's standard specifications as of the delivery date to K-C's authorized distributors/direct purchasers and are warranted for the following periods from end user's date of purchase (verified by valid sales receipt) (a) five years for Balder Technology auto darkening filters; (b) two years for all other auto darkening filters; and (c) one year for powered air purifying respirators; (2) comply with all K-C labeling representations; and (3) are manufactured in compliance with all applicable federal, state, and local laws in effect at the time and place of manufacture of the products. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. K-C is not liable for any kind of special, incidental, or consequential damages. K-C's liability for breach of contract, tort or other cause of action shall not exceed the product purchase price. Purchasers and users are deemed to have accepted the above warranty and limitation of liability, and cannot change the terms by verbal agreement or by any writing not signed by K-C. To the extent required by applicable law, K-C does not limit its liability for death/injury resulting from K-C's negligence.



Exceptional Workplaces

Rev: Nov 2013