

# LOCTITE<sup>®</sup> Frekote<sup>®</sup> C-600<sup>™</sup>

Known as Aqualine<sup>®</sup> C-600<sup>™</sup>  
October 2015

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> Frekote<sup>®</sup> C-600<sup>™</sup> provides the following product characteristics:

|                         |   |
|-------------------------|---|
| <b>Technology</b>       | Mold Release  |
| Appearance              | Milky white emulsion <sup>LMS</sup>   |
| Chemical Type           | Water based emulsion  |
| Odor                    | Mild  |
| <b>Cure</b>             | Room temperature cure   |
| Cured Thermal Stability | ≤315 °C   |
| <b>Application</b>      | Release Coatings  |
| Application Temperature | 20 to 40 °C   |
| Specific Benefit        | <ul style="list-style-type: none"><li>• Non-flammable</li><li>• Autoclaved resistant at either 121°C or 177°C</li><li>• Multiple releases</li></ul> |

LOCTITE<sup>®</sup> Frekote<sup>®</sup> C-600<sup>™</sup> mold release agent is a proprietary, water based emulsion originally developed for releasing large scale parts such as wind blades, and is ideal for numerous other high performance composite structures. When fully cured, this product chemically bonds to the mold surface to form a thin, inert, thermally stable coating. LOCTITE<sup>®</sup> Frekote<sup>®</sup> C-600<sup>™</sup> is designed to be applied and cured at ambient shop temperatures.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 20 °C 0.97 to 1.03<sup>LMS</sup>  
Flash Point - See SDS

## TYPICAL PROPERTIES OF CURED MATERIAL

4 total coats applied @ 22°C, 5 minute cure per coat, and final 30 minute cure @ 22°C  
Epoxy Release Test ≥5<sup>LMS</sup>

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

### Mold Preparation

#### Cleaning:

Mold surfaces must be thoroughly cleaned and dried. All traces of prior release must be removed. This may be accomplished by using Loctite<sup>®</sup> Frekote<sup>®</sup> PMC or other suitable cleaner. Loctite<sup>®</sup> Frekote<sup>®</sup> 915WB<sup>™</sup> or light abrasives can be used for heavy build-up.

### Directions for use:

1. Wipe on a smooth, thin continuous, wet film.
2. Wait 1-2 minutes before the coating is fully dried, then lightly wipe off the coated surface with a new wipe.
3. Allow a minimum of 15 minutes before applying next coat. Apply a minimum of 3 coats in this manner. Dampen cloth lightly as needed.
4. Allow the final coat to cure for 30 minutes at 22°C.
5. The release agent can also be spray applied. Wiping off is not necessary. 2-3 coats are needed for a new mold. One coat is needed for touch-ups. Curing between coats is 5-10 minutes, until the coating dries. The final curing time is 30 minutes.

### Mold Touch up

Touch up coats should only be applied to areas where poor release is noticed and should be applied using the same method as base coats. This will reduce the possibility of release agent or polymer build-up. The frequency of touch ups will depend on the polymer type, mold configuration, and abrasion parameters.

### Loctite Material Specification<sup>LMS</sup>

LMS dated July 30, 2009. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.** Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 0.2

Americas  
+860.571.5100

Europe  
+49.89.320800.1800

Asia  
+86.21.2891.8863

**For the most direct access to local sales and technical support visit [www.henkel.com/industrial](http://www.henkel.com/industrial)**