

**Ablestik™****ABLEBOND® 8700K**

March 2009

**PRODUCT DESCRIPTION**

ABLEBOND® 8700K provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance</b>	White
<b>Cure</b>	Heat cure
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• Non-conductive</li> <li>• Excellent adhesion</li> </ul>
<b>Application</b>	Die attach
<b>Substrates</b>	Gold
<b>Typical Assembly Applications</b>	Hybrid components

ABLEBOND® 8700K adhesive provides excellent adhesion to thin film and thick film gold surfaces. This adhesive retains its dispensed height after cure, without slumping.

**MIL-STD-883**

ABLEBOND® 8700K meets the requirements of MIL-STD-883, Method 5011.

**TYPICAL PROPERTIES OF UNCURED MATERIAL**

Viscosity @ 25 °C, mPa·s (cP)	45,000
Work Life @ 25°C, days	30
Shelf Life @ -40°C (from date of manufacture), year	1
Flash Point - See MSDS	

**TYPICAL CURING PERFORMANCE****Cure Schedule**

1 hour @ 175°C

**Alternative Cure Schedule 1**

2 hours @ 160°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

**TYPICAL PROPERTIES OF CURED MATERIAL****Physical Properties:**

Coefficient of Thermal Expansion :	
Below Tg, ppm/°C	20
Above Tg, ppm/°C	55
Glass Transition Temperature (Tg) by TMA, °C	165

Thermal Conductivity @ 121°C, W/mK	0.5
Extractable Ionic Content, ppm:	
Chloride (Cl-)	≤50
Sodium (Na+)	≤10
Potassium (K+)	≤5
Weight Loss @ 300°C, %	0.35
Moisture Absorption @ Saturation, wt.% @ 85°C/85%RH	1.98

**Electrical Properties:**

Volume Resistivity, ohms-cm	3×10 <sup>14</sup>
-----------------------------	--------------------

**TYPICAL PERFORMANCE OF CURED MATERIAL**

Die Shear Strength:

2 X 2 mm Gold, kg-f,

Substrate	@25°C
Gold	≥5000

**GENERAL INFORMATION**

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

**THAWING:**

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
4. DO NOT re-freeze. Once thawed to -40°C, the adhesive should not be re-frozen.

**DIRECTIONS FOR USE**

1. Thawed adhesive should be immediately placed on dispense equipment for use.
2. If the adhesive is transferred to a final dispensing reservoir, care must be exercised to avoid entrapment of contaminants and/or air into the adhesive.
3. Adhesive must be completely used within the product's recommended work life.

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.



**Storage**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: -40 °C. Storage below minus (-)40 °C or greater than minus (-)40 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

**Note**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1