

LOCTITE STYCAST EE 4183 HD 3537

January 2015

PRODUCT DESCRIPTION

LOCTITE STYCAST EE 4183 HD 3537 provides the following product characteristics:

Technology	Epoxy
Appearance, Resin (Component A)	Tan Liquid
Components	Two components - requires mixing
Appearance, Hardener (Component B)	Amber
Appearance (cured)	Tan
Mixing Ratio, by weight Component A: Component B	100 : 43
Product Benefits	<ul style="list-style-type: none"> Enhanced resistance to temperature cycle degradation
Cure	Heat cure
Application	Encapsulation, Potting

LOCTITE STYCAST EE 4183 HD 3537 is a flexible, low temperature cure epoxy system resistant to thermal and mechanical shock.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties *LOCTITE STYCAST EE 4183*

Filler Content %	50
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP): Spindle 6, speed 4 rpm	80,000
Specific Gravity @ 25°C	1.5
Shelf Life @ 25°C (from date of shipment), days	180
Flash Point - See SDS	

Part B Properties *STYCAST HD 3537*

Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP): Spindle 2, speed 20 rpm	900
Specific Gravity @ 25°C	1.2
Shelf Life @ 25°C (from date of shipment), days	360
Flash Point - See SDS	

Mixed Properties

Viscosity, Brookfield, 70 °C, mPa·s (cP): Spindle 2, speed 20 rpm	400
Pot life @ 70°C, 200 gram mass, hours	2
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Cure Schedule

3 hours @ 120°C plus 16 hours @ 160°C

Alternate Cure Schedule

2 hours @ 125°C, plus 2 hours @ 150°C, plus 6 hours @ 200°C

The above cure profiles are guideline recommendations. Cure

conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

All measurements are taken at 25°C, unless otherwise noted.

Physical Properties

Coefficient of Linear Thermal Expansion, ppm/°C	40.6×10 ⁻⁶
Density, lb/cu in	0.045
Heat Deflection Temperature @ 264 psi, °C	165
Linear Shrinkage, %	1.0
Moisture Absorption, 24 hrs immersion, %	0.3
Specific Gravity	1.45
Thermal Conductivity, cal x cm/sec x cm ² x °C	7×10 ⁻⁴

Electrical Properties

Volume Resistivity :	
@ 25°C	3×10 ¹⁵
@ 105°C	3×10 ¹⁵
@ 160°C	8×10 ¹²
@ 200°C	2×10 ¹⁰
Dielectric Strength @ 10 mil thickness, volts/mil	650
Dielectric Constant / Dissipation Factor:	
@ 100 Hz:	
@ 25°C	3.5/0.004
@ 105°C	3.6/0.005
@ 160°C	3.8/0.02
@ 200°C	5.3/0.235
@ 100 KHz:	
@ 25°C	3.5/0.015
@ 105°C	3.5/0.0006
@ 160°C	3.6/0.007
@ 200°C	4.0/0.052
Guide to operating class, IEEE	180

TYPICAL PERFORMANCE OF CURED MATERIAL

All measurements are taken at 25°C, unless otherwise noted.

Miscellaneous

Compressive Strength	N/mm ² 193 (psi) (28,000)
Flexural Strength	N/mm ² 107 (psi) (15,600)
Tensile Strength	N/mm ² 68 (psi) (9,950)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

- The mix ratio of LOCTITE STYCAST EE 4183 HD 3537 is fixed by their chemistry. Any attempt to increase or decrease cure rate by adding more or less hardener will result in degraded

materials.

- Crystals may form in STYCAST HD 3537 on standing. Heat both components to 71°C. Mix and deair.
- Cast into molds preheated to 70°C.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

Optimal Storage : 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F

kV/mm x 25.4 = V/mil

mm / 25.4 = inches

N x 0.225 = lb/F

N/mm x 5.71 = lb/in

psi x 145 = N/mm²

MPa = N/mm²

N·m x 8.851 = lb·in

N·m x 0.738 = lb·ft

N·mm x 0.142 = oz·in

mPa·s = cP

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is

applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1