

# LOCTITE STYCAST EE 4215/HD 3404

June 2018

## PRODUCT DESCRIPTION

LOCTITE STYCAST EE 4215/HD 3404 provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance (cured)</b>	Black
<b>Components</b>	Two components - requires mixing
<b>Mix Ratio, by volume - Part A: Part B</b>	100 : 9
<b>Mixing Ratio, by weight Component A: Component B</b>	100 : 5.5
<b>Cure</b>	Heat cure
<b>Application</b>	Potting and Encapsulating

LOCTITE STYCAST EE 4215/HD 3404 is an undiluted, silica filled epoxy casting compound, which exhibits improved thermal properties, lower shrinkage and lower expansion characteristics. The undiluted resin exhibits a higher heat distortion, lower moisture absorption, lower shrinkage and lower expansion characteristics than obtainable with a diluted resin.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties

Color	Black
Filler Content, %	48 to 52
Density, @ 25 °C, g/cm <sup>3</sup>	1.5 to 1.65
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 6, speed 4 rpm	60,000 to 100,000

### Part B Properties

Color, maximum	Gardner 2
Filler Content, %	0
Density, @ 25 °C, g/cm <sup>3</sup>	0.97 to 0.99
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 1, speed 2 rpm	18 to 34

### Mixed Properties

Pot Life @ 25 °C, minutes:	
200 g mass	20
Peak Exotherm Temperature, °C:	
200 g mass	100
Gel Time @ 25 °C, minutes	25
Viscosity @ 25 °C, mPa·s (cP)	10,500
Viscosity @ 40 °C, mPa·s (cP)	4,000

## TYPICAL CURING PERFORMANCE

### Recommended Curing Conditions

2 hours @ 60 °C (Recommended cure)
24 hours @ 22 °C (Alternate cure)

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties :

Coefficient of Thermal Expansion ASTM D7012, K <sup>-1</sup> :	
Pre Tg (Alpha 1)	47×10 <sup>-6</sup>
Post Tg (Alpha 2)	136×10 <sup>-6</sup>
Coefficient of Thermal Conductivity, ASTM C177, W/(m·K)	0.549
Shore Hardness, ISO 868, Durometer D	87
Density, @ 25 °C, g/cm <sup>3</sup>	1.66
Linear Shrinkage, ASTM D792, %	0.38
Filler Content, %	48
Heat Deflection Temperature @ 1.8 N/mm <sup>2</sup> , °C	100
Izod Impact Strength, N/mm of notch	0.04
Water Absorption, ISO 62, %:	
24 hours in water @ 25 °C	0.07
Guide to Operating Class, IEEE °C	105
Elongation, ISO 527-2, %	1.2
Tensile Strength, ISO 527-2	N/mm <sup>2</sup> 62.1
	(psi) (9,000)
Compressive Strength, ISO 604	N/mm <sup>2</sup> 117.2
	(psi) (17,000)
Flexural Strength, ISO 178	N/mm <sup>2</sup> 90.3
	(psi) (13,100)

### Electrical Properties:

Dielectric Breakdown Strength IEC 60243-1, kV/mm	59.8
Arc Resistance, ASTM D495, seconds	183
Volume Resistivity, IEC 60093, Ω·cm:	
@ 25 °C	8×10 <sup>15</sup>
@ 105 °C	1×10 <sup>14</sup>
Dielectric Constant / Dissipation Factor, IEC 60250:	
@ 25 °C:	
100 Hz	4.1 / 0.007
1 kHz	4.0 / 0.011
100 kHz	3.8 / 0.02
@ 105 °C:	
100 Hz	4.6 / 0.016
1 kHz	4.5 / 0.009
100 kHz	3.4 / 0.014

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**DIRECTIONS FOR USE**

LOCTITE STYCAST EE 4215 may crystallize during prolonged storage, if stored below 10°C. If crystallization does occur, warm the contents of the shipping container to 50 to 60°C until all crystals have dissolved. Shipping container must be loosely covered during the warming stage to prevent any pressure build-up.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8°C to 28°C. Storage below 8°C or greater than 28°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$   
 $\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$   
 $\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$   
 $\text{mPa} \cdot \text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 2