

### PRODUCT DESCRIPTION

C 400 provides the following product characteristics:

<b>Technology</b>	Cored solder wire
<b>Application</b>	Halogen free soldering

### FEATURES AND BENEFITS

- Halogen-free flux, with no intentionally added halogen
- Halogen-free flux: passes IC with pretreatment as per IPC-TM-650, EN14582
- Clear residues
- Good wetting on copper and brass
- Heat stable - low fuming
- Mild odour
- Available in a range of alloys
- Fast soldering

### PRODUCT RANGE

C 400 cored solder wire has been specially formulated to complement no clean wave and reflow soldering processes. LOCTITE® C 400 wires provide fast soldering on copper, brass, and solder coated materials.

C 400 cored wires are available in a variety of alloys conforming to J-STD-006 and EN 29453 or alloys conforming to similar national or international standard. For details refer to document "Properties of Alloys used in Cored Solder Wires".

C 400 cored wires are manufactured with a flux content between 2.2 and 3%. Alternative flux contents and alloys may be manufactured to special order.

### TECHNICAL SPECIFICATION

A full description of test methods and detailed test results are available on request.

**Alloys:** The alloys used for C 400 flux cored solder wires conform to the purity requirements of the common national and international standards. A wide range of wire diameters is available manufactured to close dimensional tolerances. For details refer to document "Properties of Alloys used in Cored Solder Wires".

**Flux:** C 400 solid flux is based on a blend of carefully selected activators and modified resin. It has a mild rosin odour and leaves a small quantity of clear, pale residue.

### TYPICAL PROPERTIES

#### Solder Alloy

Harima Code	Alloy	Melting Point, °C
60EN	Sn60Pb40	183 to 188
Sn63	Sn63Pb37	183
Sn62	Sn62Pb36Ag2	179
SAV1	Sn50Pb48.5Cu1.5	183 to 215
99C	Sn99.3Cu0.7	227
96S	Sn96.5Ag3.5	221
96SC	Sn95.5Ag3.8Cu0.7	217
97SC	Sn96.5 Ag3.0 Cu0.5	217
90ISC	Sn90.85Ag3.8Cu0.7Bi 3.0Sb1.5Ni0.15	205 to 218

#### Flux Properties

Acid Value, mgKOH/g	200
Halide Content, Cl %	0
Flux Content, %	2.2 to 3.0

### RELIABILITY PROPERTIES

Test	Specification	Results
Corrosion	DTD-599A	Pass
	J-STD-004 (10 day)	Pass
Copper Mirror	J-STD-004	Pass
Chromate paper	J-STD-004	Pass
Surface Insulation Resistance (SIR)	J-STD-004	Pass
	Bell TR-NWT-000078 issue 3	Pass
Electromigration	Bell TR-NWT-000078 issue 3	Pass
	EN 14582	Pass
Halogen Content	EN 14582	Pass
Activity	EN29454	1.1.3
Classification	IPC-SF-818	LR3CN

### DIRECTIONS FOR USE

Soldering with C 400 does not require any special methods or deviation from standard hand soldering practices

**Soldering Iron:**

Good results should be obtained using a range of tip temperatures. However, the optimum tip temperature and heat capacity required for a hand soldering process is a function of both soldering iron design and the nature of the task. Care should be exercised to avoid unnecessarily high tip temperatures for excessive times. A high tip temperature will increase any tendency to flux spitting and it may produce some residue darkening. The soldering iron tip should be properly tinned and this may be achieved using **C 400** cored wire. Severely contaminated soldering iron tips should first be cleaned and pre-tinned using TTC-LF Tip Tinner/Cleaner, then wiped on a clean, damp sponge before re-tinning with **C 400** cored wire.

**Soldering Process:**

**C 400** cored wires contain a careful balance of resins and activators to provide clear residues, maximum activity and high residue reliability without cleaning in most situations. To achieve the best results from **C 400** solder wires, recommended working practices for hand soldering should be observed as follows:

- Apply the soldering iron tip to the work surface, ensuring that it simultaneously contacts the base material and the component termination to heat both surfaces properly. This process should only take a fraction of a second.
- Apply **C 400** flux cored solder wire to a part of the joint surface away from the soldering iron and allow to flow sufficiently to form a sound joint fillet – this should be virtually instantaneous. Do not apply excessive solder or heat to the joint as this may result in dull, gritty fillets and excessive or darkened flux residues.
- Remove solder wire from the work piece and then remove the iron tip. The total process will be very rapid, depending upon thermal mass, tip temperature and configuration and the solderability of the surfaces to be joined. The flux system is designed to leave relatively low residues and to minimize residual activity. This is achieved by ensuring some decomposition and volatilization takes place during the soldering process.
- **C 400** flux cored solder wires provide fast soldering on copper and brass surfaces as well as solder coated materials. The good thermal stability of **C 400** flux cored solder wire means it is also well suited to soldering applications requiring higher melting lead free alloys.

**Cleaning:**

**C 400** flux cored solder wires have been formulated to leave pale flux residues and to resist spitting and fuming. In most industrial and consumer electronics applications, cleaning will not be required. The product may therefore be used to complement a no-clean wave soldering or reflow process or to allow repairs to cleaned boards without the need for a second cleaning process.

If cleaning is required this is best achieved using MCF800 solvent cleaner (see separate technical data sheet). Other proprietary solvent or semi-aqueous processes may be suitable. Saponification may be suitable but customers must ensure that the desired level of cleanliness can be achieved by their chosen system.

**STORAGE AND SHELF LIFE****Storage:**

It is recommended to store **C 400** in a dry environment at room temperature.

**Shelf Life:**

The cored solder wire is classified as a non-shelf life item. Thus, no expiry date is required to be printed on the labels. However, the quality and manufacturing records for cored solder wire is only maintained no longer than 2 years from the date of manufacture. Thus, any quality feedback after that stipulated period cannot be addressed.

**DATA RANGES**

The data contained herein may be reported as a typical value and/or a range. Values are based on actual test data and are verified on a periodic basis.

**GENERAL INFORMATION**

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

**Not for Product Specifications**

The technical information contained herein is intended for reference only. Please contact your nearest HARIMA location for assistance and recommendations on specifications for this product.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

NOT FOR PRODUCT SPECIFICATIONS

THE TECHNICAL INFORMATION CONTAINED HEREIN IS INTENDED FOR REFERENCE YOUR NEAREST HARIMA LOCATION FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT.



**Disclaimer**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. HARIMA is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**Japan :**

**Harima Chemicals, Inc. (Head Office)**  
3-8-4 Nihonbashi, Chuo-ku, Tokyo 103-0027  
TEL +81-3-5205-3040

**Europe :**

**Harimatec Czech, s.r.o.  
(Head Office/Plant)**  
PointPark Prague D8, hala DC03, Zdibsko 614,  
Klecany 25067, Czech Republic  
TEL +420-284-688-922

**Americas :**

**Harimatec Inc. (Head Office/Plant)**  
1965 Evergreen Blvd., Suite 400, Duluth,  
GA 30096, U.S.A.  
TEL +1-678-325-2926

**UK :**

**HARIMA UK LTD. (R&D)**  
Wood Lane End, Hemel Hempstead,  
Hertfordshire, HP2 4RQ UK  
TEL +44-1442-962464

**APAC :**

**Harimatec Malaysia Sdn. Bhd.  
(Head Office/Kuala Lumpur Plant)**  
22, Jalan PJU 3/48, Sunway Damansara,  
47810 Petaling Jaya, Selangor, Malaysia  
TEL +60-3-7804-9495

**Ipoh Plant**

Lot 62049, Jalan Portland Tasek Industrial  
Estate, 31400 Ipoh, Perak, Malaysia  
TEL +60-5-543-2000

**CHINA :**

**Harimatec Hangzhou Co., Ltd.  
(Head Office/Plant)**  
No.15 Gaoxin 5 Road, Hongda Road,  
Qiaonan-Qu, Xiaoshan Economic  
and Technological Development Zone,  
Hangzhou, Zhejiang 311231, China  
TEL +86-571-2286-8518

