

MF R301

June 2022

PRODUCT DESCRIPTION

MF R301 provides the following product characteristics:

Technology	No-clean liquid flux
Application	Wave soldering

MF R301 is a no-clean high activity, resin-based halide-free liquid flux designed particularly for use on surfaces with poor solderability.

FEATURES AND BENEFITS

- Lead free and tin-lead compatible
- Fast soldering on conventional leaded and SMD components - no bridges or icicles
- Exceptional through-hole penetration
- Sustained performance for maximum process window
- No cleaning - reduces costs
- Minimal residues to interfere with ATE probes without cleaning
- Compatible with rosin-based surface preservatives
- Foam, spray or wave applications

APPLICATIONS

MF R301 is recommended for consumer electronics and general electrical soldering applications using conventional wave soldering machines. The activator package is designed to enhance efficacy, especially when soldering to poorly preserved substrates/components. A small amount of rosin is complemented by the solvent package to ensure optimum drainage characteristics at the exit of the wave, minimising bridges, spiking and mid-pad solder balling. This leaves a small amount of non-corrosive residue.

TECHNICAL SPECIFICATION

MF R301 can be applied by foam, spray or wave.

TYPICAL PROPERTIES

Flux Properties

Solids Content, %	6.0
Halide Content, Cl %	Zero
Acid Value, mgKOH/g	40
Specific Gravity @ 25°C	0.802
Colour	Pale amber
Thinner	PC70i

RELIABILITY PROPERTIES

Test	Specification	Results
Chromate Paper	J-STD-004	Pass
Surface	J-STD-004	Pass
Insulation		
Resistance (SIR)		
Electromigration	Telcordia GR-78-Core	Pass
Flux Activity	J-STD-004	ROM0
Classification	EN29454	1.1.3

RECOMMENDED OPERATING CONDITIONS

The Printed Circuit Board:

MF R301 is recommended for use on copper or solder coated PCBs. It will solder satisfactorily over most rosin-based preservatives. It is recommended that the rosin based preservative be applied no longer than 3 months before soldering, since the period of protection is limited dependent on storage conditions. **MF R301** has been formulated to work over a wide range of solder resists.

Machine Preparation:

Ensure the soldering machine is thoroughly cleaned, including all fingers, pallets and conveyors, so that any possible contamination has been removed. MCF 800 Cleaner can be used in the finger cleaning system.

Fluxing

MF R301 has been formulated for use in foam, spray or wave fluxers in the same way as ordinary fluxes on standard wave soldering machines.

For foam fluxing, it is important to remove excess flux from the circuit boards using the standard air knife or brushes supplied on the wave soldering machine.

An air pressure of about 5-7 psi is recommended and the nozzle should be about 25mm below the board and angled back at a few degrees, perpendicular to the plane of the board. This will ensure effective removal of excess flux without transferring droplets to the top of the following board.

Sufficient space should be allowed between the foam fluxer and the air knife to prevent the air stream from disturbing the foam.

Observing the following instructions will help ensure optimum foaming and soldering results.

NOT FOR PRODUCT SPECIFICATIONS

THE TECHNICAL INFORMATION CONTAINED HEREIN IS INTENDED FOR REFERENCE YOUR NEAREST HARIMA LOCATION FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT.

1. Use **Dry Air**.
2. Keep the flux tank **FULL** at all times.
3. The top of the foaming stone should be no more than 2cm below the surface of the liquid flux. A fine foaming stone is preferred and if necessary, raise the level of the stone.
4. The preferred width of the slot (opening) of the foam fluxer is 10mm. If it is wider and problems are encountered reduce the opening to 10mm. It is preferable to have a chimney for the foam which tapers towards the top.
5. **DO NOT** use hot fixtures or pallets as these cause the foam to deteriorate and increase losses by evaporation.
6. **DO NOT** use fixtures that have the potential to entrap flux.

The upper limit for flux coverage to ensure that soldered PCBs pass cleanliness tests is 25g.m² of circuit. Good soldering can be achieved at half this volume. It is important to prevent deposition of excess flux and overspray on to the top side of the circuit.

DO NOT use fixtures which can entrap the flux. This may lead to random solder balling caused by the sudden volatilisation of the trapped flux upon contact with the solder wave.

It is strongly recommended that DRY air be used in the spraying process. Fitting a topside canopy over the preheater/s can help to produce more effective drying and activation. This will allow the use of faster conveyor speeds and improve soldering.

Wave Soldering:

1. Excess moisture on the PCB during soldering may lead to random solder balling and poor wetting of some solder joints.
2. IT IS IMPORTANT that the flux solvent carrier is fully evaporated and that the PCB appears virtually dry when it reaches the solder wave.
3. At a speed of 1.5m min⁻¹ (5ft min⁻¹) a contact length of 38 to 50 mm between the solder wave and the PCB is recommended. At lower speeds, this contact length should be reduced. Very slow speeds through the solder wave may produce dull solder joints.
4. It is recommended to use a temperature profiling system to measure preheat and peak temperatures during set up of the wave soldering machine and for consistent process monitoring.
5. **MF R301** flux can be used with all standard solder alloys. The recommended maximum solder bath temperature is 250°C for leaded alloys. Temperatures as high as 275 to 280°C may be necessary for some lead-free alloys. Temperatures as low as 235°C in tin-lead soldering and 245°C in lead free may be used in some situations and this results in improved soldering and less wastage through dross formation.
6. Dwell time on the wave should be 0.5 to 1.0 seconds (chip wave) and 2.0 to 3.0 seconds (laminar wave). Conveyor speed for dual wave systems should be at least 1.2m min⁻¹.

IT IS IMPORTANT that flux solvent be removed by the preheat and that the **PCB IS NOT WET** when it reaches the solder wave.

Cleaning:

MF R301 is designed as a no-clean flux, however some applications may require board cleaning for which MCF 800 cleaner may be used. Boards soldered with **MF R301** flux pass MIL-P-28809A ionic contamination test without cleaning provided excess flux is not applied and a clean system and components are used. It is recommended that the soldering system itself be tested for cleanliness using an unfluxed board passed over the soldering machine. Suppliers should be requested to supply clean components and clean boards. For a completely no-clean process, use no-clean cored solder wire and/or no clean solder paste. These products also generate low levels of VOC emissions due to their low flux content and heat stable resins. Soldering iron tips should be kept clean with TTC-LF Tip Tinner/Cleaner (data sheet available).

Flux Control:

Control of the flux concentration is achieved in the normal manner by measuring the temperature and specific gravity of the flux. A nomograph is available to show how these measurements are related to the corrective action needed.

The specific gravities of the flux and thinners are similar and they vary with water contents. As a result, flux concentration control by measurement of the acid value is more convenient.

Preheating

As **MF R301** contains more solvent than conventional rosin fluxes, it will be necessary to adjust the preheater setting to remove the additional solvent and to ensure that the flux is properly activated. The optimum preheat temperature and time for a PCB depends on its design and the thermal mass of the components but the cycle should be sufficient to ensure that the flux coating is not visibly wet when it contacts the wave. Combinations which have given good results are shown below.

Conveyor Speed	Topside preheat temperature °C (°F)
0.9m min ⁻¹ (3ft min ⁻¹)	80 to 85 (176 to 185)
1.2m min ⁻¹ (4ft min ⁻¹)	85 to 90 (185 to 194)
1.5m min ⁻¹ (5ft min ⁻¹)	95 to 100 (203 to 212)

STORAGE AND SHELF LIFE

Storage:

It is recommended to store **MF R301** in a dry environment at room temperature, away from sources of ignition.

Shelf Life:

Provided **MF R301** is stored as recommended above a shelf life of 2 years can be expected.

DATA RANGES

The data contained herein may be reported as a typical value and/or a range. Values are based on actual test data and are verified on a periodic basis.

NOT FOR PRODUCT SPECIFICATIONS

THE TECHNICAL INFORMATION CONTAINED HEREIN IS INTENDED FOR REFERENCE YOUR NEAREST HARIMA LOCATION FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT.



GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Not for Product Specifications

The technical information contained herein is intended for reference only. Please contact your nearest HARIMA location for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. HARIMA is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

Japan :

Harima Chemicals, Inc. (Head Office)
 3-8-4 Nihonbashi, Chuo-ku, Tokyo 103-0027
 TEL +81-3-5205-3040

Europe :

Harimatec Czech, s.r.o. (Head Office/Plant)
 PointPark Prague D8, hala DC03, Zdibsko 614,
 Klecany 25067, Czech Republic
 TEL +420-284-688-922

Americas :

Harimatec Inc. (Head Office/Plant)
 1965 Evergreen Blvd., Suite 400, Duluth,
 GA 30096, U.S.A.
 TEL +1-678-325-2926

UK :

HARIMA UK LTD. (R&D)
 Wood Lane End, Hemel Hempstead,
 Hertfordshire, HP2 4RQ UK
 TEL +44-1442-962464

APAC :

Harimatec Malaysia Sdn. Bhd. (Head Office/Kuala Lumpur Plant)
 22, Jalan PJU 3/48, Sunway Damansara,
 47810 Petaling Jaya, Selangor, Malaysia
 TEL +60-3-7804-9495

Ipoh Plant

Lot 62049, Jalan Portland Tasek Industrial
 Estate, 31400 Ipoh, Perak, Malaysia
 TEL +60-5-543-2000

CHINA :

Harimatec Hangzhou Co., Ltd. (Head Office/Plant)
 No.15 Gaoxin 5 Road, Hongda Road,
 Qiaonan-Qu, Xiaoshan Economic
 and Technological Development Zone,
 Hangzhou, Zhejiang 311231, China
 TEL +86-571-2286-8518

