



Features

- Partition set is adjustable for different size parts. Fits into the [37750](#), [37760](#) and [37762](#) Tek Trays
- Impregnated corrugated material; greater durability than coated or printed material
- Static dissipative surface resistance of 1×10^6 to $< 1 \times 10^9$ ohms per ANSI/ESD STM11.11
- Made from 100% recycled material, and is 100% recyclable
- Reusable, ensuring best value

Cell Height	Cell Length	Cell Width	# of Long Partitions	# of Short Partitions	Cell Total
1-1/2"	2-11/16"	2-1/8"	3	7	32
1-1/2"	2-11/16"	4-3/8"	3	3	16
1-1/2"	2-11/16"	6-5/8"	3	2	8
1-1/2"	2-11/16"	8-7/8"	3	1	8
1-1/2"	5-9/16"	2-1/8"	1	7	16
1-1/2"	5-9/16"	4-3/8"	1	3	8
1-1/2"	5-9/16"	6-5/8"	1	2	4
1-1/2"	5-9/16"	8-7/8"	1	1	4

Meets the required limits of ANSI/ESD S20.20, and Packaging standard ANSI/ESD S541.

SPECIFICATIONS

Properties

Surface Resistance

Discharge Shielding

Sloughing Test

Recyclability

Typical Values

1×10^6 to $< 1 \times 10^9$ ohms

< 50 nanoJoules

Negligible surface damage at 10 cycles and $< 5\%$ of surface damage at 200 cycles in Taber Abrasion Test.

No conductive particles abraded from surface

Complete recyclability of package

Test Procedures/Method

ANSI/ESD STM11.11

ANSI/ESD STM 11.31

ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992



Made in the
United States of America

Specifications and procedures subject to change without notice.

Tolerances are +/- 10% unless otherwise specified

PROTEKTIVE PAK
BURIED SHIELDING LAYER

TEK-TRAY PARTITION SET

PROTEKTIVE PAK
13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE (909) 627-2578
ProtektivePak.com

DRAWING NUMBER
37764

DATE:
October
2019